

Technical data SONO WZ

Sensoren design	Probe dimension
Probe head SONO WZ: High Grade Steel 1.4301 with ceramic window. SONO DIS Measurement device: Robust aluminium case.	Sensor: 154 x 60mm (length x width) Suitable for temperatures up to 50°C.
Measurement range water content	Measurement range conductivity
The sensor covers water content ranges of different types of concrete for liquid concrete. Accuracy of up to 1-3 Liter/m³ is achievable.	The radar-based conductance EC TRIME can be measured in a range of 0...50mS/cm, dependent on concrete type or cement type.
Power supply	Measurement field expansion
4.8V-DC, 2000mAh Battery capacity is sufficient for up to 500 measurements per charge.	Approximately 40 - 80 mm, depending on material and moisture.
Calibration	Statistical analysis
SONO WZ is already delivered with a universal calibration which provide reliable results for most used concrete types. It is possible to adjust the SONO DIS with a correction value for measuring special concrete types like fibre concrete.	The SONO DIS carries out an internal statistical analysis during the single moisture measurements. With and single measurement values an average value and the standard deviation StdDev is calculated and displayed. This ensures a qualitative statement for accuracy and representativity already during the measurement procedure.

SONO WZ  
the Water/Cement Analyzer for Fresh Concrete



Based on the revolutionary TRIME radar technology, it is possible for the first time to determine the water content of fresh concrete quickly, precisely and directly on site.



Concrete-Laboratory certified acc. to  
DIN EN ISO/IEC 17025

„After more than 150 performed tests we are so convinced of the quality of the SONO-WZ, that we are able to waive additional tests with the kiln-drying procedure in our factory production control system. Therefore, for us this means a considerably simplified work with significant reduction of time.“

Vladimir Naumann, Head of Test Body,  
mbl Cement and Concrete Laboratory, Germany



High-qualified research and knowledge institute in the building sector and specialist in the concrete and asphalt sector:

„With specializing in concrete and with most modern laboratories, we have tested SONO-WZ in various concrete types. Tests were also made at low and high concrete temperatures. To avoid possible errors with kiln-drying, we have produced all mixtures with dry aggregates. We are impressed about the good accordance of the water/cement-values of our concrete recipes which were measured in comparison with the SONO-WZ.“

Wilko van der Meer, Director,  
BIAIS Research & Technology, Netherland

Contact

IMKO Micromodultechnik GmbH  
Am Reutgraben 2  
76275 Ettlingen  
Germany

Tel +49 7243 5921 0  
info@imko.de

www.imko.de



Moisture Sensor Experts





# The new dimension of quality control directly on site

Higher security and preventing expensive damages – with the new water/cement analyzer SONO WZ.

The quality of fresh concrete is crucial for stability and durability of concrete buildings. Of particular importance are the two parameters water content and water/cement ratio in order to achieve the required quality. Up to now, cumbersome and time-consuming samples had to be kiln dried and the water/cement ratio must be determined with material log records.

SONO WZ can determine the water content, directly on site. A determination of the radar based electrical conductivity EC TRIME allows an evaluation of the used cement type. Simply place the innovative lance probe inside the fresh concrete and achieve reliable measurement results within 1 to 2 minutes.



SONO WZ can be adjusted to special concrete recipes. In recent decades concrete types have been optimized with different additives, like self-compacting concrete, fair faced concrete, lightweight concrete, heavy concrete and others. This variety of different concrete types can be covered by SONO WZ.

SONO WZ works with state-of-the-art TRIME TDR-method (Time-Domain-Reflectometry) based on guided radar technology. In long-term collaboration with scientific institutions the TRIME technology was established with scientific discoveries and new, innovative and patented methods. Based on the radar method, SONO WZ allows an evaluation of the used cement type by detecting the electrical conductivity EC TRIME which can be interpreted as a raw value for a cement pre-analysis. This new and innovative method is a contribution to a greater security for the control of fresh concrete. With the SONO probe whose measurement field penetrates deep inside the material and also high-end concrete can be measured easily. An automatic averaging with 4 to 8 single measurements ensures the measurement of a representative material mix. Due to the structured working method with SONO WZ, precise and reliable results are displayed within few minutes.

### Kiln drying

Measured material:

**3 kg**

30 min

### SONO WZ

Measured material:

**20 kg**

2 min



## At last to finish the slow and laborious kiln drying!

The innovative and scientifically established method sets new standards!

- Precise measurement of water content of fresh concrete mixtures. As user you will obtain the water content in liter per m³ by considering of the mass density entered by hand inside the SONO DIS measurement device.
- Determination of the radar based electrical conductivity EC TRIME which allows an evaluation of the used cement type. As user you can thus quickly see what is going on concerning the used cement type and if this value corresponds to the expected exposure class.
- SONO WZ is already delivered with a universal calibration which provides reliable results for most used concrete types.
- Both durable and waterproof construction of SONO WZ and SONO DIS ensures safe handling even under difficult environmental conditions.

## The measurement with evaluation

After entering the adjustable parameters, the SONO DIS can be switched to the measurement mode. Immerse SONO WZ in the fresh concrete and perform single measurements by pressing the button.

EC Trime

standard deviation

▲ set parameters		C start meas.	
▼ clear last meas.			
WaterCont.:		164,5	l/m³
EC-T:	25,5	dS/m	Last: 167,3 l/m³
Std.Dev.:	0,2	😊	No. Values: 7

water content

the last value

**Easy handling:**  
Simply place the innovative lance probe SONO WZ inside the fresh concrete. After 4 to 8 single measurements with the SONO DIS device, an automatic averaging ensures precise results within 1 to 2 minutes – directly on site.